

TECHNICAL DATA : foam 354

FOAMTYPE	polyurethaan, polyether	
QUALITY	354	
COLOR	light blue	
GROSS DENSITY	35	
PIECE DENSITY	33	
COMPRESSION HARDNESS	5.4	at 40 % pressure
INDENTATION HARDNESS	180	25 %
	220	40 %
	415	65 %
ORIGIN	Belgium	

Density	ISO 845	kg/m ³
Compression hardness (=CLD)	ISO 3386/1	kPa
Indentation hardness (=ILD)	2439/B	Newton

Free of CFK.

Sixinch cannot be held responsible for further treatment.

Fiche technique : **foam 354**

FOAMTYPE	polyurethaan, polyether	
QUALITE	354	
COULEUR	bleu	
DENSITE BRUT	35	
DENSITE NET	33	
RESISTANCE A LA COMPRESSION	5.4	CLD 40 %
DURETE PAR INDENTATION	180	25 %
	220	40 %
	415	65 %
PRODUCTION EN	Belgique	

densité	ISO 845	kg/m ³
compression (=CLD)	ISO 3386/1	kPa
dûrité (=ILD)	ISO 2439/B	Newton

100% libre de CFK.

Sixinch ne peut pas être rendu responsable lors de transformation de la matière.

BETREFT : technische fiche foam **354**

FOAMTYPE	polyurethaan, soort polyether / versneden blokschuim		
KWALITEIT	354		
KLEUR	blauw		
BRUTODENSITEIT	35		
NETTODENSITEIT	33		
DRAAGVERMOGEN	5.4	bij	40 % indruk
COMPRESSIEWEERSTAND	180		25 %
	220		40 %
	415		65 %
HERKOMST	België		

densiteit (=soortelijk gewicht)	volgens ISO 845	in kg/m ³
compressieweerstand (=CLD)	volgens ISO 3386/1	in kPa
draagvermogen (=ILD)	volgens ISO 2439/B	in Newton

Dit schuim is volgens een CFK-vrij proces aangemaakt.
Sixinch kan niet verantwoordelijk worden gesteld bij verdere behandeling of verwerking.